

gloveon Paloma



Nitrile Exam Gloves Powder Free, Standard Cuff

Like the purity of a white Dove, **Paloma**, our white nitrile gloves offers the elegance of touch and feel with strength and dexterity needed for the delicate procedure and jobs.



GloveOn Paloma		
Length (mm)	≥ 230	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.07 ± 0.02	
Finger (13mm ± 3mm from tip)	0.09 ± 0.02	
Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.50
Physical Dimensions	S2	4.00
Tensile Strength	S2	4.00
Visual Inspection (Major)	S4	2.50
Visual Inspection (Minor)	S4	4.00
Particulate Residue	N = 5	≤ 2mg/glove

REORDER CODE

NTR51XS	X-SMALL
NTR51SS	SMALL
NTR51MM	MEDIUM
NTR51LL	LARGE
NTR51XL	X-LARGE

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Standard cuff
- White colour

PACKAGING

200 gloves per box for XS to L
180 gloves per box for XL
10 boxes per carton

REGULATORY COMPLIANCE

TGA - ARTG 164563, FDA 510(k),
MDD 93/42/EEC, REACH,
ROHS Directive 2002/95/EC, EC 10/2011,
REGULATION (EC) No 1935/2004,
PPE 89/686/EEC

STANDARDS

ASTM D6319, EN 455 part 1, 2, 3 & 4,
EN 1186, EN 13130, CEN/TS 14234,
EN 420, EN 374 part 1, 2 & 3

MANUFACTURING ACCREDITATIONS

ISO 9001:2008
ISO 13485:2003
EN ISO 13485:2003

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05 Test Report PN 116668)

Chemotherapy Drug and Concentration	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	15.1 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	15.4 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Paloma nitrile glove at 15.1 minutes and 15.4 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

A brand by



Mun Australia
Toll free: 1800 456 837 (GLOVES)
info.au@munglobal.com



Protection Always On

NITRILE EXAMINATION GLOVES

GLOVEON Paloma - Powder Free - FDA 510K



NITRILE	0.07mm	3.5G	230mm	100	
----------------	---------------	-------------	--------------	------------	--

Material Thickness Weight (M) Length Pcs / Box Latex Free



Personal Protection



Hospital / Dental



Laboratory / Pharmacy



Food Contact



Cleaning



Beauty / Body Art

DESCRIPTION

Donning these gloves is like putting on a second skin. The superior tactility lends to delicate procedures and any functional use with and assurance of tensile strength and resistance to chemicals.

FEATURES

Material	Nitrile
Type	Medical Examination
Sterile	No
Powder Free	Yes
Latex Free	Yes
Beaded Cuff	Yes
Ambidextrous	Yes
Colour	White
Outer Surface	Finger Textured
Length	230 mm
Weight (M)	3.5g ± 0.2g
Single Wall	Yes
Thickness - Palm	0.07 mm
Thickness - Fingers	0.09 mm
Sizes	S / M / L / XL

STANDARDS & ACCREDITATIONS

FDA 510K

ASTM D6319, EN 455 part 1, 2, 3 & 4 (Chemo)

EN 1186, EN 13130, CEN/TS 14234

EN 420, EN 374 part 1, 2 & 3

MDD 93/42/EEC, REACH

CE

ISO 9001:2008, ISO 13485:2003, EN ISO 13485:2003

PPE (EU)

PACKAGING

Box Size	100 Pcs / Box
Case Size	10 Boxes / Case (0.59 kg)

MANUFACTURING

Brand	GloveOn
Manufactured	Malaysia



SourceWeb Medical

office@sourceweb-medical.ag

